

CYCOLOYTM RESIN LG9000

REGION ASIA

DESCRIPTION

PC/ABS low gloss.

TYPICAL PROPERTY VALUES

Revision 20190214

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	54	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	75	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	84	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2300	MPa	ASTM D 790
Hardness, Rockwell R	118	-	ASTM D 785
IMPACT			
Izod Impact, notched, 23°C	534	J/m	ASTM D 256
Izod Impact, notched, -30°C	320	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	40	J	ASTM D 3763
Instrumented Impact Total Energy, -30°C	33	J	ASTM D 3763
THERMAL			
Vicat Softening Temp, Rate B/50	129	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	123	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	107	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	129	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	110	°C	ASTM D 648
CTE, -20°C to 150°C, flow	7.2E-05	1/°C	ASTM E 831
CTE, -20°C to 150°C, xflow	7.2E-05	1/°C	ASTM E 831
Thermal Conductivity	0.2	W/m-°C	ASTM C 177
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
PHYSICAL			
Specific Gravity	1.13	-	ASTM D 792
Water Absorption, 24 hours	0.1	%	ASTM D 570
Water Absorption, equilibrium, 23C	0.4	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 260°C/5.0 kgf	17	g/10 min	ASTM D 1238
OPTICAL			
Gloss, untextured, 60 degrees	30	-	ASTM D 523
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating	1.49	mm	UL 94
INJECTION MOLDING			
Drying Temperature	105 – 110	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	275 – 300	°C	
Nozzle Temperature	275 – 300	°C	
Front - Zone 3 Temperature	260 – 300	°C	
Middle - Zone 2 Temperature	255 – 295	°C	
Rear - Zone 1 Temperature	250 – 290	°C	
Mold Temperature	60 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	30 – 80	%	
Vent Depth	0.038 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.