

CYCOLOYTM RESIN MC8800

REGION ASIA

DESCRIPTION

PC/ABS, high heat, high impact, low CTE.

TYPICAL PROPERTY VALUES

Revision 20190207

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	55	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	58	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	9	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	120	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	96	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2960	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	427	J/m	ASTM D 256
Izod Impact, notched, -30°C	106	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	56	J	ASTM D 3763
Instrumented Impact Energy @ peak, -30	50	J	ASTM D 3763
THERMAL			
Vicat Softening Temp, Rate B/50	117	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	137	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	120	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	126	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.66E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.1E-05	1/°C	ASTM E 831
Thermal Conductivity	0.2	W/m-°C	ASTM C 177
PHYSICAL			
Specific Gravity	1.22	-	ASTM D 792
Water Absorption, 24 hours	0.1	%	ASTM D 570
Water Absorption, equilibrium, 23C	0.4	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.6	%	SABIC method
Melt Flow Rate, 230°C/3.8 kg	1.4	g/10 min	ASTM D 1238
Melt Flow Rate, 260°C/5.0 kgf	10	g/10 min	ASTM D 1238
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	280 – 300	°C	
Nozzle Temperature	270 – 300	°C	
Front - Zone 3 Temperature	270 – 300	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Middle - Zone 2 Temperature	265 – 290	°C	
Rear - Zone 1 Temperature	260 – 270	°C	
Mold Temperature	75 – 100	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	30 – 80	%	
Vent Depth	0.038 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.