

LNPTM STAT-KONTM COMPOUND TX06488

TX06488

REGION AMERICAS

DESCRIPTION

LNP STAT-KON TX06488 is a compound based on Polyurethane resin containing Proprietary Filler(s). Added features of this grade are: Excellent Ductility, Electrically Conductive.

TYPICAL PROPERTY VALUES

Revision 20181012

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|-----------------|-------------------|--------------|
| MECHANICAL | | | |
| Tensile Stress, yld, Type I, 5 mm/min | 19 | MPa | ASTM D 638 |
| Tensile Stress, brk, Type I, 5 mm/min | 18 | MPa | ASTM D 638 |
| Tensile Strain, yld, Type I, 5 mm/min | 388 | % | ASTM D 638 |
| Tensile Strain, brk, Type I, 5 mm/min | 392 | % | ASTM D 638 |
| Tensile Modulus, 5 mm/min | 60 | MPa | ASTM D 638 |
| Flexural Modulus, 1.3 mm/min, 50 mm span | 60 | MPa | ASTM D 790 |
| IMPACT | | | |
| Multiaxial Impact | 41 | J | ISO 6603 |
| Instrumented Impact Total Energy, 23°C | 39 | J | ASTM D 3763 |
| THERMAL | | | |
| HDT, 0.45 MPa, 3.2 mm, unannealed | 23 | °C | ASTM D 648 |
| HDT, 1.82 MPa, 3.2mm, unannealed | 23 | °C | ASTM D 648 |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm | 23 | °C | ISO 75/Bf |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm | 23 | °C | ISO 75/Af |
| PHYSICAL | | | |
| Specific Gravity | 1.28 | - | ASTM D 792 |
| Density | 1.28 | g/cm ³ | ASTM D 792 |
| Moisture Absorption, 50% RH, 24 hrs | 0.67 | % | ASTM D 570 |
| Mold Shrinkage, flow, 24 hrs | 0.8 – 1 | % | ASTM D 955 |
| Mold Shrinkage, xflow, 24 hrs | 0.4 – 0.6 | % | ASTM D 955 |
| Moisture Absorption (23°C / 50% RH) | 0.89 | % | ISO 62 |
| ELECTRICAL | | | |
| Surface Resistivity | 1.E+02 – 1.E+05 | Ohm | ASTM D 257 |

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.