

# LNP<sup>TM</sup> STAT-KON<sup>TM</sup> COMPOUND VC108

REGION ASIA

## DESCRIPTION

LNP<sup>TM</sup> STAT-KON<sup>TM</sup> Compound VC108.

## TYPICAL PROPERTY VALUES

Revision 20181231

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yield	98	MPa	SABIC - Japan Method
Tensile Strain, break	3 – 3	%	SABIC - Japan Method
Flexural Stress	148	MPa	ASTM D 790
Flexural Modulus	5980	MPa	ASTM D 790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	39	J/m	ASTM D 256
<b>THERMAL</b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	199	°C	ASTM D 648
CTE, -30°C to 30°C	0.00008 – 0.00008	1/°C	TMA
<b>PHYSICAL</b>			
Specific Gravity	1.43	-	ASTM D 792
Water Absorption, 24 hours	0.07	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.3 – 0.5	%	SABIC method
Mold Shrinkage, flow, 6.4 mm	0.8 – 1	%	SABIC method
<b>ELECTRICAL</b>			
Surface Resistivity	1.E+08 – 1.E+12	Ohm	ASTM D 257

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.