

LNPTM STAT-KONTM COMPOUND WX11322

REGION ASIA

DESCRIPTION

PBT base, CF+Glass fiber filled, Halogen FR V-0, Low warpage

TYPICAL PROPERTY VALUES

Revision 20181231

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	143	MPa	SABIC - Japan Method
Tensile Strain, break	9	%	SABIC - Japan Method
Flexural Stress, yield, 6.4 mm	208	MPa	ASTM D 790
Flexural Modulus, 6.4 mm	11600	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	78	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 6.4 mm, unannealed	205	°C	ASTM D 648
PHYSICAL			
Specific Gravity	1.54	-	ASTM D 792
Mold Shrinkage, flow, 1.5-3.2 mm	0.17	%	SABIC method
Mold Shrinkage, xflow, 1.5-3.2 mm	0.55	%	SABIC method
ELECTRICAL			
Surface Resistivity	9.E+07	Ohm	ASTM D 257
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating	2	mm	UL 94
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	12	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 265	°C	
Nozzle Temperature	245 – 260	°C	
Front - Zone 3 Temperature	250 – 265	°C	
Middle - Zone 2 Temperature	245 – 260	°C	
Rear - Zone 1 Temperature	240 – 255	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.