

LNPTM STAT-KONTM COMPOUND ZE004

ZC-1004
REGION ASIA

DESCRIPTION

LNP* STAT-KON* ZE004 is a compound based on PPO resin containing 20% Carbon Fiber. Added feature of this grade includes: Electrically Conductive.

TYPICAL PROPERTY VALUES

Revision 20181231

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	80	MPa	ASTM D 638
Tensile Stress, break	104	MPa	ASTM D 638
Tensile Strain, break	0.5	%	ASTM D 638
Tensile Modulus, 50 mm/min	24820	MPa	ASTM D 638
Flexural Stress	179	MPa	ASTM D 790
Flexural Modulus	24130	MPa	ASTM D 790
Tensile Stress, yield	54	MPa	ISO 527
Tensile Stress, break	103	MPa	ISO 527
Tensile Strain, break	0.9	%	ISO 527
Tensile Modulus, 1 mm/min	14720	MPa	ISO 527
Flexural Stress	151	MPa	ISO 178
Flexural Modulus	12700	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	299	J/m	ASTM D 4812
Izod Impact, notched, 23°C	37	J/m	ASTM D 256
Izod Impact, unnotched 80*10*4 +23°C	17	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	4	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	139	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	137	°C	ASTM D 648
CTE, -40°C to 40°C, flow	4.86E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	3.6E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	4.8E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	3.7E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	141	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	135	°C	ISO 75/Af
PHYSICAL			
Density	1.17	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs	0.2 – 0.4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.4 – 0.6	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs	0.3	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	0.53	%	ISO 294
Density	1.17	g/cm ³	ISO 1183

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
ELECTRICAL			
Surface Resistivity	1.E+02 – 1.E+06	Ohm	ASTM D 257
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	4	hrs	
Melt Temperature	300 – 305	°C	
Front - Zone 3 Temperature	300 – 310	°C	
Middle - Zone 2 Temperature	290 – 300	°C	
Rear - Zone 1 Temperature	275 – 290	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.