

SEMICOSIL® 989/1K



1-part heat-curing silicone rubber

SEMICOSIL® 989/1K is a non-slump, thermally curable, addition curing one-part silicone rubber.

Properties

- one-part, ready-to-use
- thixotropic
- transparent
- medium hardness
- high flexibility
- rapid heat curing
- primerless adhesion to many substrates

Specific features

- 1-part heat-curing
- Addition-curing

Technical data

General Characteristics

Property	Condition	Value	Method
Density	23 °C	approx. 1.1 g/cm ³	DIN 53479
Viscosity, dynamic	25 °C 0.5 1/S	300000 mPa·s	DIN EN ISO 3219
Viscosity, dynamic	25 °C 25 1/S	30000 mPa·s	DIN EN ISO 3219

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Uncured

Property	Condition	Value	Method
Color	-	transparent	-
Density	-	approx. 1.07 g/cm ³	DIN EN ISO 1183-1
Viscosity, dynamic (shear rate = 0,5 s ⁻¹)	25 °C	300000 mPa·s	DIN EN ISO 3219
Viscosity, dynamic (shear rate = 25 s ⁻¹)	25 °C	300000 mPa·s	DIN EN ISO 3219

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Cured

Cured for 30 min at 150 °C in a circulating air oven

Property	Condition	Value	Method
Color	-	transparent	-
Density	23 °C	approx. 1.07 g/cm ³	DIN EN ISO 1183-1
Elongation at break	-	200 %	ISO 37
Hardness Shore A	-	55	ISO 868
Tensile strength	-	5 N/mm ²	ISO 37

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Automotive Electronics
- Electrics & Electronics
- Bonding, Fixing & Sealing
- Power Electronics

Application details

- general purpose adhesive for the electronics industry
- FIPG applications

Processing

Surface preparation

All surfaces must be clean and free of contaminants that will inhibit the cure of SEMICOSIL® 989/1K. Examples of inhibiting contaminants are sulfur containing materials, plasticizers, urethanes, amine containing materials and organometallic compounds – especially organotin compounds. If a substrate's ability to inhibit cure is unknown, a small scale test should be run to determine compatibility.

Temperature	Curing time, thickness 1 cm
100 °C	6 h
130 °C	1 h
150 °C	10 min

Dispensing

Because of the thixotropy (shear thinning effect) SEMICOSIL® 989/1K can be dispensed easily with all dispensing equipments.

To eliminate any air introduced during dispensing or trapped under components or devices a vacuum encapsulation is recommended.

SEMICOSIL® 989/1K shows good primerless adhesion to many substrates. We recommend running preliminary tests to optimize conditions for the particular application.

Curing

SEMICOSIL® 989/1K works best when cured at 115 °C or more depending on the size and heat sink properties of the components.

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

According to the latest findings, the addition-curing silicone rubber SEMICOSIL® 989/1K contains neither toxic or corrosive substances which would require special handling precautions.

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code SEMICOSIL® 989/1K



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
info@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.