

ELASTOSIL® N9111 WHITE



Moisture Curing Silicone Rubber (RTV-1)

ELASTOSIL® N9111 WHITE is non-slump, non-corrosive, alkoxy-cure one-component silicone, which cures at room temperature under the influence of atmospheric moisture.

Properties

- excellent adhesion to many substrates
- no inhibition effect to platinum-catalysed grades
- no use of organotin catalysts
- medium hardness Shore A
- flame retardant: meets UL94 V-0

Special features

- Broad adhesion profile
- Flame retardant
- High elongation
- High tear-resistant
- Non-corrosive to metals
- Non-slump
- Thixotropic
- Tin-free catalysis

Technical data

General Characteristics

Property	Condition	Value	Method
Density	25 °C	approx. 1.3 g/cm ³	-

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Uncured

Property	Condition	Value	Method
Viscosity, dynamic D = 0,5 1/s	23 °C	900000 mPa·s	ISO 3219
Viscosity, dynamic D = 25 1/s	23 °C	100000 mPa·s	ISO 3219
Color	-	white	-
Curing speed	23 °C 50 % r.h	2 mm/d	-
Skin forming time	23 °C 50 % r.h	20 - 45 min	-

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Cured

2 mm, 14 d cure time at 23 °C, 50 % rh

Property	Condition	Value	Method
Elongation at break	-	500 %	DIN 53504 S1 / ISO 37
Tensile strength	-	2.20 N/mm ²	DIN 53504 S1 / ISO 37
Hardness Shore A	-	30	DIN 53 505 / ISO 868
Density in water	23 °C	1.33 g/cm ³	DIN EN ISO 1183-1 / ISO 2781
Color	-	white	-
Tear strength	-	10 N/mm	ASTM D 624

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Automotive & Transport
- Automotive Electronics
- Measurement & Control, Sensor Technology
- Luminaires
- Heating, Ventilation, Air Conditioning (HVAC)
- Small Appliances
- Small Appliances
- Household Applications
- Household Applications
- Formed-In-Place-Gaskets (Wet Type)

Application details

Multipurpose sealant & adhesive for the appliance, automotive and electronics industry.

Processing

Due to its shear thinning nature ELASTOSIL® N9111 WHITE is easy to apply. The material starts curing upon contact to air humidity.

ELASTOSIL® N9111 WHITE shows excellent primerless adhesion to many substrates, like glass, aluminium, stainless steel, PA and PBT.

We recommend running preliminary tests to optimize conditions for the particular application.

Detailed processing instructions are given in our brochure “ROOM TEMPERATURE VULCANIZING (RTV) SILICONES - MATERIAL AND PROCESSING GUIDELINES

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

During vulcanization of ELASTOSIL® N9111 WHITE, a total of 3 % by weight of alcohol is split off. These vapours should not be inhaled for long periods or in high concentration. Work areas should therefore be well ventilated.

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code ELASTOSIL® N9111 WHITE



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
info@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.